

Method for producing biodegradable disposable tableware involves measuring out flour and natural thickeners, adding water and homogenizing the mixture through mechanical stirring. Starch is used as a thickener. Stabilization of the resulting mass is carried out on a horizontal surface. Processing is carried out in a microwave oven at a power of 600 W for 1 minute. Formation and stabilization of the finished product is carried out at a temperature of 18-25 °C for 24 hours until complete hardening.