

Method for constructing base of road surface includes steps in which aggregate is distributed, binder is added, components are moistened and mixed, and mixture is compacted. Composite mineral powder is used as binder, consisting of co-ground aggregate, dihydrate phosphogypsum, and concrete rubble powder with a particle size of less than 1 mm, in an amount of 15...30% of the aggregate mass. The phosphogypsum content is 10...20%. The content of concrete rubble powder is 10...40% of mineral powder composition.